

LAUR SILICONE

LAUR AS-2XXA SERIES SILICONE RUBBER

ANTI-STATIC SILICONE

The AS-2XXA series of materials is intended to be Anti-Static while retaining better physical properties than most conductive silicones. The conductivity values are in the range that ASTM defines as "Anti-Static", these materials are not designed for maximum electrical conductivity. These compounds are designed to be processed by calendaring or molding techniques. Processing by extrusion is possible if they are cured in a salt bath.

TYPICAL PROPERTIES

Material	AS-250A	AS-255A	AS-260A	AS-265A	AS-270A
Durometer, A-2	50	55	60	65	70
Tensile, psi (MPa)	1000 (6.9)	1025 (7.1)	1030 (7.1)	1180 (8.1)	1100 (7.6)
Elongation, %	450	400	335	345	300
Tear B, ppi (kN/m)	74 (13.0)	80 (14.0)	80 (14.0)	85 (14.9)	85 (14.9)
Volume Resistivity ¹ , Ohm*cm	6,050 6.05×10^3	8,500 8.5×10^3	7,040 7.04×10^3	15,300 1.53×10^4	4,000 4.0×10^3
Specific Gravity	1.20	1.21	1.21	1.22	1.28
Color	Black		Black	Black	Black

ALL SLABS MOLDED 10 MINUTES @ 340 °F

The properties listed here are typical values and are not intended to be used for writing specifications. For assistance in selecting a compound for a specific application, please contact our technical department.

Per ASTM D991, generally antistatic rubber products are considered to have a volume resistivity of 10^4 to $10^8 \Omega \cdot \text{cm}$. Conductive rubber products are generally considered to have a volume resistivity of less than $10^4 \Omega \cdot \text{cm}$.

Note 1 The volume resistivity values given reflect actual test values. Due to the nature of the test and the materials, these values may change more than most rubber properties.

SHELF LIFE

When stored below 90 °F, this series of materials has a shelf life of 3 months from date of sale.

AS2XXA Series

Revision: 07-16

LAUR SILICONE, INC.
4930 S. M-18, BEAVERTON, MICHIGAN 48612-9181

WWW.LAURSILICONE.COM

TELEPHONE 989-435-7400
FAX 989-435-7707

Si-Release® is a trademark owned by Laur Silicone, Inc., Beaverton, MI.