

LAUR R2880/XX SILICONE RUBBER**STRIP BUILDABLE SILICONE**

Laur R2880/XX series are general purpose, economical roller compounds that offer low price and good finished roll properties. This series of materials offers good film release and relatively good heat transfer properties. They are normally supplied in strip form, but it is possible to provide other custom packaging to meet specific needs.

TYPICAL PROPERTIES

Material	R2880/40	R2880/50	R2880/60	R2880/70	R2880/80	R2880/90
Durometer, A-2	40	50	60	70	80	89
Tensile, psi	750	800	850	900	1,020	1,020
Elongation, %	550	400	350	300	175	130
Tear B, ppi	70	90	100	100	105	N/A
Specific Gravity	1.37	1.50	1.50	1.57	1.60	1.63
Standard Color	Gray	Gray	Gray	Gray	Gray	Gray

ALL SLABS MOLDED 10 MINUTES @ 340 °F

The properties listed above are typical values and are not intended to be used for writing specifications. For assistance in selecting a compound for a specific application, please contact our technical department.

SHELF LIFE

When stored below 90 °F, this series of materials has a shelf life of 3 months from date of sale.